

CL 2207 US NA
SN 10/769881

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : C08G 18/08, 18/10, 18/65, 18/66, 18/48, C08K 5/42	A1	(11) International Publication Number: WO 00/61651	(43) International Publication Date: 19 October 2000 (19.10.00)
--	----	--	---

(21) International Application Number: PCT/US00/09968
(22) International Filing Date: 13 April 2000 (13.04.00)
(30) Priority Data:
60/129,271 14 April 1999 (14.04.99) US

(71) Applicant: THE DOW CHEMICAL COMPANY [US/US];
2030 Dow Center, Midland, MI 48674 (US).

(72) Inventors: PARKS, Franklin, E.; 7118 S. F. Austin Road,
Jones Creek, TX 77541 (US). BHATTACHARJEE, De-
bkumar; 54 Waterlily Court, Lake Jackson, TX 77566 (US).
SANCHEZ, Thelma, C.; Apartment 128, 400 Flag Lake
Drive, Lake Jackson, TX 77566 (US).

(74) Agent: JOZWIAK, Elisabeth, T.; Intellectual Property, P.O.
Box 1967, Midland, MI 48641-1967 (US).

(81) Designated States: AE, AG, AL, AM, AT, AU, AZ, BA, BB,
BG, BR, BY, CA, CH, CN, CR, CZ, DE, DK, DM, DZ,
EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN,
IS, JP, KE, KG, KR, KZ, LC, LK, LR, LS, LT, LU, LV,
MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO,
RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA,
UG, UZ, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS,
MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ,
BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE,
CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,
NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,
GN, GW, ML, MR, NE, SN, TD, TG).

Published

With international search report.
Before the expiration of the time limit for amending the
claims and to be republished in the event of the receipt of
amendments.

(54) Title: POLYURETHANE FILMS AND DISPERSIONS FOR THE PREPARATION THEREOF

(57) Abstract

A polyurethane film is disclosed, wherein the film is prepared from a polyurethane dispersion, the dispersion being prepared from a non-ionic polyurethane prepolymer, and the prepolymer being prepared from a polyurethane prepolymer formulation including a diisocyanate and an active hydrogen containing material. The dispersion is formed in a two or more step process wherein, in a first step the prepolymer is formed and, in a subsequent step, an aqueous dispersion of the prepolymer is formed, in the presence of an anionic surfactant, both steps occurring in the substantial absence of an organic solvent. A process for preparing the film and a dispersion useful in making the film are also disclosed. The present invention substantially avoids many of the handling concerns with the dispersions and films of the prior art. Moreover, the present invention is suitable for use in applications such as, for example, medical applications, including gloves, condoms, medical bags, and catheters.

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

POLYURETHANE FILMS AND DISPERSIONS FOR THE PREPARATION THEREOF

This invention relates to polyurethane films and dispersions for the preparation thereof. This invention particularly relates to polyurethane films prepared from aqueous dispersions.

5 While ostensibly reactive with water, it has long been known that polyisocyanate polymers can be used to prepare aqueous polyurethane dispersions. Polyurethane dispersions are generally prepared by chain extending the reaction product of an organic diisocyanate or polyisocyanate and an organic compound having two or more active hydrogen atoms such as polyalkylene ether glycols, poly(alkylene ether-alkylene thioether) glycols, alkyd resins, polyesters and polyester amides, often using an organic solvent. The diisocyanate is used in stoichiometric excess so that the reaction product, also referred to as a polyurethane/urea/thiourea prepolymer, is isocyanate terminated. Examples of polyurethane prepolymer preparations are described in U.S. Patents Nos. 3,178,310, 3,919,173, 4,442,259, 4,444,976, and 4,742,095, among others.

15 Polyurethane dispersions are reported as being useful for preparing such diverse materials as: coatings and bonds in U.S. Patent No. 4,292,226; flexible solvent barriers in U.S. Patent No. 4,431,763; adhesives in US 4,433,095; and films in 4,501,852. Films, or rather the process of dipping to make a film, can be a part of the processes for making many articles. Examples of film applications include gloves, organ bags, condoms, ostomy bags, and the like. While it is known that such applications can be made with polyurethane dispersions, conventional polyurethane dispersions have sometimes been found to have insufficient physical or handling properties to make them a preferred material for such applications. Also, the use of a solvent can have adverse effects for some applications.

25 Polyurethanes are the reaction product of a polyalcohol and a polyisocyanate. Typically, the polyisocyanates used to prepare polyurethane dispersions have been aliphatic isocyanates such as disclosed in US 5,494,960. Aromatic polyisocyanates such as toluene diisocyanate (TDI) and methylene diphenyldiisocyanate (MDI) as well as polymethylene polyphenylisocyanate (PMDI) are also known to be useful.

30 Films prepared from natural rubber latex are common, yet are considered to have properties which are desirable from the perspective of comfort and utility. Unfortunately, natural rubber latex also includes proteins and other materials which can be irritating to skin.

Accordingly, it would be desirable in the art of preparing polyurethane films from aqueous dispersions, to prepare such films which have physical and handling properties

sufficient for their use in conventional film applications. It would be further desirable if such films could be prepared with dispersions which are, in turn, prepared in the absence of organic solvents. It would be yet even more desirable if such films had physical properties similar to natural rubber latex films but which did not include the dermal irritants which occur
5 in natural rubber latex.

In one aspect, the present invention is a polyurethane film comprising a film prepared from a polyurethane dispersion, the dispersion being prepared from a non-ionic polyurethane prepolymer, and the prepolymer being prepared from a polyurethane prepolymer formulation including a diisocyanate and an active hydrogen containing
10 material. The dispersion is formed in a two or more step process wherein, in a first step the prepolymer is formed and, in a subsequent step, an aqueous dispersion of the prepolymer is formed, in the presence of an anionic surfactant, both steps occurring in the substantial absence of an organic solvent.

In another aspect, the present invention is a process for preparing a
15 polyurethane film comprising the steps of preparing a non-ionic polyurethane prepolymer, dispersing the prepolymer in water in the presence of an anionic surfactant, and then applying the dispersion to a substrate as a film. The prepolymer is prepared from a polyurethane prepolymer formulation including a diisocyanate and an active hydrogen containing material. The first two steps both occur in the substantial absence of an organic
20 solvent.

In still another aspect, the present invention is an aqueous polyurethane dispersion useful for preparing polyurethane films comprising the product of dispersing in water a nonionic polyurethane prepolymer prepared from a prepolymer formulation including a diisocyanate and a mixture of diols. The dispersion is formed in a two or more step
25 process wherein, in a first step the prepolymer is formed and, in a subsequent step, an aqueous dispersion of the prepolymer is formed, in the presence of an anionic surfactant, both steps occurring in the substantial absence of an organic solvent.

The present invention involves a nonionic prepolymer, external stabilization, and the substantial absence of organic solvents, thereby avoiding many of the handling
30 concerns with the dispersions and films of the prior art. Moreover, the films of the present invention do not include the dermal irritants which occur in natural rubber latex. The films and dispersions of the present invention are thus suitable for use in applications such as, for example, medical applications.

In one embodiment, the present invention is a polyurethane film prepared from a
35 polyurethane dispersion. The dispersions of the present invention can be prepared by any

method known to one of ordinary skill in the art of preparing polyurethane dispersions to be useful in making such dispersions subject to the following limitations.

The process of preparing the dispersion includes at least two steps. In a first step, a prepolymer is prepared. In a subsequent step, the prepolymer is dispersed with
5 water.

The prepolymer can be dispersed in any way which results in a dispersion which can be used to prepare a film having acceptable physical properties for the anticipated use of the film. The dispersions can be done by a batch process or by a continuous process. If done by a batch process, preferably, the dispersion is done by an inverse phase process wherein
10 a small amount of water, including a small amount of anionic surfactant, is first added to a continuous prepolymer phase and mixed and then more water is added with mixing until the phase inverts.

When dispersions of the present invention are prepared by means of a continuous process, preferably they are prepared by means of a high internal phase ratio
15 (HIPR) process. Such processes are known and are disclosed in, for Example, U.S. Patent No. 5,539,021 to Pate, et al., and WO 98/41552 A1 to Jakubowski, et al. When prepared by either method, the resulting dispersion should have a particle size sufficient to make the dispersion stable. The dispersions of the present invention will have a particle size of from 0.9 to about 0.05, preferably from about 0.5 to about 0.07 and even more preferably, from
20 about 0.4 to about 0.10 microns. Most preferably, the particle size of the dispersions of the present invention is about 0.15 microns.

The stability of the dispersion is sufficient to prevent the dispersion from coagulating under storage or shipping conditions, but not so stable that the polymer cannot be coagulated onto a substrate to prepare a film. Films are often prepared by methods that
25 include thermal and chemical coagulation. During these processes, a dispersion at the surface of a substrate is destabilized and the polymer coalesces onto the substrate forming a film. If the dispersion is so stable that it cannot be readily coagulated onto the substrate, it is not useful for forming films. On the other hand, if the dispersion is so unstable that it coagulates during storage or on shipping, it is also not useful for forming the films of the
30 present invention. While not a preferred embodiment, the emulsions of the present invention can be used in casting applications where emulsion stability is not at critical.

The polyurethane dispersions of the present invention are prepared from a nonionic polyurethane prepolymer. The nonionic prepolymers of the present invention are prepared with either an aliphatic or an aromatic diisocyanate. Preferably, the diisocyanate
35 is an aromatic diisocyanate selected from the group consisting of MDI, TDI and mixtures

thereof. TDI can be generally used with any commonly available isomer distribution. The most commonly available TDI has an isomer distribution of 80 percent of the 2,4 isomer and 20 percent of the 2,6 isomer. For the purposes of the present invention, TDI with other isomer distributions can also be used, but often at significantly higher cost.

5 When MDI is used with the formulations of the present invention, it preferably has a P,P' isomer content of from about 99 percent to about 90 percent. Even more preferably, when MDI is used with the formulations of the present invention, it preferably has a P,P' isomer content of from about 98 to about 92 percent. Most preferably, when MDI is used with the formulations of the present invention, it preferably has a P,P' isomer
10 content of about 94 percent. While MDI with such isomer distributions can be prepared by distillation during the MDI process, it can also be prepared by admixing commonly available products such as ISONATE 125M* and ISONATE 50OP*. (*ISONATE 125M and ISONATE 50OP are trade designations of The Dow Chemical Company.)

 When mixtures of TDI and MDI are used to prepare the prepolymers of the
15 present invention, they are admixed in a ratio of MDI to TDI of from about 99 percent MDI to about 80 percent MDI. More preferably, when mixtures of TDI and MDI are used to prepare the prepolymers of the present invention, they are admixed in a ratio of MDI to TDI of from about 98 percent MDI to about 90 percent MDI. Most preferably, when mixtures of TDI and MDI are used to prepare the prepolymers of the present invention, they are admixed in a
20 ratio of MDI to TDI of about 96 percent MDI. Preferably the prepolymers of the present invention are prepared with MDI or mixtures of MDI and TDI. Even more preferably, the prepolymers of the present invention are prepared with MDI as the only aromatic diisocyanate.

 In one embodiment of the present invention, the prepolymers of the present
25 invention are prepared from a formulation that includes an active hydrogen containing material. In a preferred embodiment of the present invention, the active hydrogen containing material is a mixture of diols. One component of the diol mixture is a high molecular weight polyoxypropylene diol having an ethylene oxide capping of from 0 to 25 weight percent. The other component of the diol mixture is a low molecular weight diol.
30 The polyether diols of the formulations of the present invention can be prepared by any method known to those of ordinary skill in the art of preparing polyether polyols to be useful for preparing such diols. Preferably, the polyether diols are prepared by the alkoxylation of a difunctional initiator in the presence of a basic catalyst. For example, a polyether useful with the present invention is a product resulting from a two step alkoxylation of ethylene

glycol with first propylene oxide and then ethylene oxide, in the presence of KOH as a catalyst.

The high molecular weight polyether diol component of the diol mixture of the prepolymer formulations of present invention is preferably a polyoxypropylene diol having an ethylene oxide capping of from 0 to 25 weight percent. Preferably, the molecular weight of this component is from about 1,000 to about 4,000, more preferably from about 1,200 to about 2,500, and most preferably from about 1,800 to about 2,200. As stated, the polyether diol is capped with from 0 to 25 percent ethylene oxide. Preferably, the high molecular weight diol is capped with from about 5 to about 25 percent ethylene oxide, and more preferably, from about 10 to about 15 percent ethylene oxide.

The low molecular weight diol component of some of the prepolymer formulations of the present invention can also be a product of alkoxylating a difunctional initiator. Preferably, this component is also a polyoxypropylene diol, but it can also be a mixed ethylene oxide propylene oxide polyol, as long as at least 75 weight percent of the alkoxides used, if present, is propylene oxide. Diols such as propylene glycol, diethylene glycol, dipropylene glycol, and the like, can also be used with the formulations of the present invention. The low molecular weight diol component of the prepolymer formulations, if present, has a molecular weight of from about 60 to about 750, preferably from about 62 to about 600, and most preferably, from about 125 to about 500.

The prepolymers of the present invention can be prepared in any way known to those of ordinary skill in the art of preparing polyurethane prepolymers to useful for preparing such prepolymers. Preferably the aromatic diisocyanate and polyether diol mixture are brought together and heated under reaction conditions sufficient to prepare a polyurethane prepolymer. The stoichiometry of the prepolymer formulations of the present invention is such that the diisocyanate is present in excess. Preferably, the prepolymers of the present invention have an isocyanate content (also known as %NCO) of from about 1 to about 9 weight percent, more preferably from about 2 to about 8 weight percent, and most preferably from about 3 to about 7 weight percent.

The prepolymers of the present invention are optionally extended with a difunctional amine chain extender when the active hydrogen containing material of the prepolymer formulation is a mixture of a low molecular weight diol and a high molecular weight polyether diol. The difunctional amine chain extender is not optional but required when the active hydrogen containing material of the prepolymer formulation is a high molecular weight polyether diol and does not include a low molecular weight diol. Preferably, the difunctional amine chain extender is present in the water used to make the

dispersion. When used, the amine chain extender can be any isocyanate reactive diamine or amine having another isocyanate reactive group and a molecular weight of from about 60 to about 450, but is preferably selected from the group consisting of: an aminated polyether diols; piperazine, aminoethylethanolamine, ethanolamine, ethylenediamine and mixtures thereof. Preferably, the amine chain extender is dissolved in the water used to make the dispersion.

The prepolymers of the present invention are nonionic. There are no ionic groups incorporated in or attached to the backbones of the prepolymers used to prepare the films of the present invention. The anionic surfactant used to prepare the dispersions of the present invention is a external stabilizer and is not incorporated into the polymer backbones of the films of the present invention.

The prepolymers of the present invention are dispersed in water which contains a surfactant. Preferably the surfactant is an anionic surfactant. In the practice of preparing the dispersions of the present invention, the surfactant is preferably introduced into water prior to a prepolymer being dispersed therein, but it is not outside the scope of the present invention that the surfactant and prepolymer could be introduced into the water at the same time. Any anionic surfactant can be used with the present invention, but preferably the anionic surfactant is selected from the group consisting of sulfonates, phosphates, carboxylates. More preferably, the anionic surfactant is sodium dodecyl benzene sulfonate, sodium dodecyl sulfonate, sodium dodecyl diphenyl oxide disulfonate, sodium n-decyl diphenyl oxide disulfonate, isopropylamine dodecylbenzenesulfonate, or sodium hexyl diphenyl oxide disulfonate, and most preferably, the anionic surfactant is sodium dodecyl benzene sulfonate.

The dispersions of the present invention can have a solids level of from about 30 weight percent to about 60 weight percent. Films will not necessarily be prepared from dispersions having this level of solids. While the dispersions themselves will be stored and shipped at as high a solids content as possible to minimize storage volume and shipping costs, the dispersions can desirably be diluted prior to final use. The thickness of the film to be prepared and the method of coagulating the polymer onto a substrate will usually dictate what solids level is needed in the dispersion. When preparing films, the dispersions of the present invention can be at a weight percent solids of from 5 to about 60 percent, preferably from about 10 to about 40 percent, and, most preferably, from about 15 to about 25 weight percent when preparing examination gloves. For other applications, the film thickness and corresponding solids content of the dispersion used can vary.

For many film applications, it is necessary that the polymer used have physical properties similar to the more conventional materials used in those applications. The desired physical properties will depend largely on the end use application. For example, for an exam glove application, the films of the present invention can have a tensile set of less than 5%.

5 One significant advantage of the films of the present invention over natural latex in applications such as exam gloves is that the films of the present invention have significantly lesser risk of inducing an allergic reaction in those wearing the gloves. Another benefit of films of the present invention is that they can be prepared such that they are self-releasing. In the art of preparing exam gloves, this ability is also known as "powder free" in
10 reference to the fact that such gloves are occasionally prepared and sold with a layer of talcum powder, corn starch, or the like, to keep the polymer from adhering to itself, thereby making it easier to put on the gloves.

The films of the present invention can be made self releasing by inclusion of a wax in the prepolymer formulation. Preferably the wax is carnauba wax and the like. It is
15 preferable that the wax to be used be selected from those that are not likely to induce an allergic reaction in skin that comes in contact therewith. Therefore, food grade waxes are particularly preferred for this application. When used, the waxes are preferably included in the water used to disperse the prepolymer formulation at a concentration of from about 0.1 to about 2 weight percent.

20 In addition to the waxes already mentioned, other additives can be included in the films of the present invention. Any additive which is known to those of ordinary skill in the art of preparing films from dispersion to be useful can be used with the films of the present invention so long as their presence does not degrade the properties of the film so much that the film is no longer fit for its intended purposes. The additives can also be
25 incorporated into the films in any way known to be useful including, but not limited to inclusion in the prepolymer formulation and inclusion in the water used to make the dispersion. For example titanium dioxide is useful for coloring films of the present invention. Other useful additives include calcium carbonate, silicon oxide, defoamers, biocides, carbon particles, and the like.

30 The films of the present invention are advantageously applied to a substrate using techniques which are commonly known, such as salt coagulation, thermal coagulation, casting, and combinations thereof. Coagulation processes are described generally in, for example, Japanese Kokai 2/1/1990, assigned to Daiichi Kogyo Seiyaku K.K., and salt coagulation in particular is generally described in WO 96/08352, assigned to
35 Jackson et al.

Often the shape of the substrate will determine the end use of the film. Substrates can be made from any of the materials commonly used in the art of preparing films. Suitable substrate materials include, for example, metals, porcelain and plastics. Metals include, for example, steel, aluminum, and titanium.

5 The present invention has applicability in, for example, gloves, condoms, medical bags, angioplasty balloons, medical bellows, face masks, blood pressure cuffs and the like. The present invention also has applicability in parts associated with drug delivery mechanisms, including catheters, medical tubing, gaskets and o-rings. Moreover, the present invention has applicability in many non-medical items, such as, for example, non-
10 medical gloves, swim caps, tool handle grips, industrial caps and plugs, windshield wiper boots, toy balloons, toys, electrical parts, covers and gaskets.

The following examples are for illustrative purposes only and are not intended to limit the scope of the claimed invention. Percentages are in weight percents unless otherwise stated.

15 EXAMPLES

The following materials are used in the examples below:

- Polyether Polyol is a 2000 molecular weight polyoxypropylene diol having 12.5 percent ethylene oxide end capping.
- Low Molecular Weight Diol is a 425 molecular weight all polyoxypropylene diol.
- 20 • Polyisocyanate A is MDI having a 4,4' isomer content of 98 percent and an isocyanate equivalent weight of 125.
- Polyisocyanate B is MDI having a 4,4' isomer content of 50 percent and an isocyanate equivalent weight of 125.
- Surfactant is 22 percent solution of sodium dodecyl benzene sulfonate in water.
- 25 • Diamine is a 230 molecular weight polyoxypropylene diamine.

Example 1

A polyurethane prepolymer is prepared by admixing 52.0 parts of Polyether Polyol and 14.7 parts of Low Molecular Weight Diol and then heating the admixture to 50°C. This material is then admixed with 33.3 parts of Polyisocyanate A which has also been
30 warmed to 50°C. A small amount of benzoyl chloride is added to neutralize residual base in the polyols. The admixture is then heated at 70°C for 4 hours and then tested to determine NCO content. The NCO content is 5.75 percent.

A polyurethane dispersion is prepared by admixing 200g of the prepolymer admixed with 13g water and 38g surfactant using a high shear mixer running at about 2500

rpm. Additional water is slowly added until a phase inversion is observed. Additional water is added until the solids content is 40 percent.

A film is then prepared by a coagulation process by heating a steel plate in an oven until it reached a temperature of from 100 to 120°F (38-49°C). The plate is then
5 dipped into a 20 percent solution of calcium nitrate in 1:1 by weight of water and methanol which also included about 1 wt % of a ethoxylated octylphenol surfactant. The plate is then placed into an oven at 230°F (110°C) for approximately 15 minutes to form a very thin film of calcium nitrate on the plate. The plate is allowed to cool to 105°F (40°C) and then dipped into the polyurethane dispersion diluted to 23% solids with deionized water and removed
10 (total dwell time is approximately 20 sec). The plate is held for 5 minutes at room temperature to allow the film to generate enough gel strength, followed by leaching in a water bath at 115°F (46°C) for 10 minutes. Both sides of the plate is then sprayed with water at 115°F (40°C) for two additional minutes. The plate is then heated to 230°F (110°C) for 30 minutes and then cooled to ambient temperature. A polyurethane film is peeled from
15 the substrate and tested using ASTM Designation D 412-98a (Die C; overall length = 4.5", width of narrow section = 0.25", and gauge length = 1.31") Testing results are presented in the table. It is tactilely soft and yet has good physical properties.

Example 2

A polyurethane dispersion is prepared by dispersing the prepolymer of Example
20 1 as in Example 1 except that the water added to the dispersion after the phase inversion includes Diamine at a concentration of 0.25 equivalent stoichiometry based on available isocyanate content). The polyurethane dispersion was then diluted to 23% solids and coagulated according to the procedure described in the Example 1.

Examples 3 and 4

25 These polyurethane prepolymers are prepared substantially similarly to the procedure in Example 1 except that the prepolymer compositions are changed as indicated in the table, and the prepolymers are reacted with water and surfactant as described in the Example 1. The polyurethane dispersions are then diluted to 23% solids and coagulated according to the procedure described in the Example 1.

30 Example 5

A polyurethane prepolymer and dispersion are prepared substantially similarly to Example 4 except that the water added to the dispersion after the phase inversion includes Diamine at a concentration of 0.25 NCO stoichiometry. The polyurethane dispersion was then diluted to 23% solids and coagulated according to the procedure described in the
35 Example 1.

TABLE

EXAMPLE	1	2	3	4	5
POLYETHER POLYOL (parts by wt)	52	52	53	52	52
LOW MWT DIOL (parts by wt)	14.7	14.7	15	14.7	14.7
POLYISOCYANATE A (parts by wt)	33.3	33.3	17	29.1	29.1
POLYISOCYANATE B (parts by wt)	--	--	15	4.2	4.2
%NCO	5.75	5.75	5.40	5.80	5.80
Chain extension	Water	Diamine (0.25 stoichiometry)	Water	Water	Diamine (0.25 stoichiometry)
TENSILE (PSI)	5830	4342	2604	4976	3020
ELONGATION AT BREAK (%)	644	747	995	672	783
STRESS AT 100% ELONGATION (PSI)	421	247	173	398	192

1. A polyurethane film comprising a film prepared from a polyurethane dispersion, the dispersion being prepared from a non-ionic polyurethane prepolymer, and the prepolymer being prepared from a polyurethane prepolymer formulation including a diisocyanate and an active hydrogen containing material wherein:
 - 5 the dispersion is formed in a two or more step process wherein,
 - (1) in a first step the prepolymer is formed and, in a subsequent step,
 - (2) an aqueous dispersion of the prepolymer is formed, in the presence of an anionic surfactant, both steps occurring in the substantial absence of an organic solvent.
- 10 2. The polyurethane film according to Claim 1, wherein the diisocyanate is either:
 - (a) an aliphatic diisocyanate; or
 - (b) an aromatic diisocyanate selected from the group consisting of MDI, TDI, and mixtures thereof.
3. The polyurethane film according to Claim 1, wherein the active hydrogen
15 containing material is either:
 - (a) a mixture of a high molecular weight diol and a low molecular weight diol; or
 - (b) a high molecular weight diol, wherein when the active hydrogen containing
20 material does not include a low molecular weight diol, the prepolymer is dispersed in water which includes a difunctional amine chain extender.
4. The polyurethane film according to Claim 3 wherein the high molecular weight diol is a high molecular weight polyoxypropylene diol having an ethylene oxide capping of from 0 to 25 percent.
5. The polyurethane film according to Claim 1 wherein the anionic surfactant is
25 sodium dodecyl benzene sulfonate.
6. The polyurethane film according to Claim 1 wherein the dispersion has a particle size of from 0.9 microns to 0.05 microns.
7. The polyurethane film according to Claim 1 wherein the dispersion has a solids content of from 5 to 60 weight percent.
- 30 8. The film of Claim 1, wherein the film has a shape of a glove, a condom, an angioplasty balloon, a medical bag or a catheter.
9. A process for preparing a polyurethane film comprising the steps of:
 - (a) preparing a non-ionic polyurethane prepolymer;
 - (b) dispersing the prepolymer in water in the presence of an anionic surfactant;
35 and then

- (c) applying the dispersion to a substrate as a film;
wherein the prepolymer is prepared from a polyurethane prepolymer formulation including a diisocyanate and an active hydrogen containing material; and
wherein steps (a) and (b) both occur in the substantial absence of an organic solvent.
- 5 10. The process according to Claim 9, wherein the diisocyanate is either:
(a) an aliphatic diisocyanate; or
(b) an aromatic diisocyanate selected from the group consisting of MDI, TDI, and mixtures thereof; and
10 the active hydrogen containing material is either:
(a) a mixture of a high molecular weight diol and a low molecular weight diol; or
(b) a high molecular weight diol;
- 15 wherein when the active hydrogen containing material does not include a low molecular weight diol, the prepolymer is dispersed in water which includes a difunctional amine chain extender.
11. The process according to Claim 9 wherein step (c) comprises dipping, thermal coagulation, casting, electrodeposition, or a combination thereof.
- 20 12. The process of Claim 9 wherein the shape of the substrate is such that the resulting film is in the shape of a glove, condom, angioplasty balloon, medical bag, medical tubing, or catheter.
13. An aqueous polyurethane dispersion useful for preparing polyurethane films comprising the product of dispersing in water a nonionic polyurethane prepolymer prepared from a prepolymer formulation including a diisocyanate and a mixture of diols wherein:
25 the dispersion is formed in a two or more step process wherein,
(1) in a first step the prepolymer is formed and, in a subsequent step,
(2) an aqueous dispersion of the prepolymer is formed, in the presence of an anionic surfactant, both steps occurring in the substantial absence of an organic solvent.
- 30 14. The dispersion of Claim 13, wherein the diisocyanate is either:
(a) an aliphatic diisocyanate; or
(b) an aromatic diisocyanate selected from the group consisting of MDI, TDI, and mixtures thereof.
15. The dispersion of Claim 13, wherein the mixture of diols is a mixture of a high
35 molecular weight diol and a low molecular weight diol.

16. The dispersion of Claim 15 wherein the high molecular weight diol is a polyoxypropylene diol with an ethylene oxide capping of from 0 to 25 percent.
17. The dispersion of Claim 13, wherein the dispersion has a particle size of from 0.9 microns to 0.05 microns.
- 5 18. The dispersion of Claim 13 wherein the dispersion has a solids content of from 5 to 60 weight percent.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 00/09968

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08G18/08 C08G18/10 C08G18/65 C08G18/66 C08G18/48
C08K5/42

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C08G C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 98 41554 A. (DOW CHEMICAL CO) 24 September 1998 (1998-09-24) page 16, line 22 -page 17, line 35; claims 1,3-7,11,14; examples 1,12,13; table	1-7,9, 10,13-18
A	US 4 507 413 A (THOMA WILHELM ET AL) 26 March 1985 (1985-03-26) column 6, line 43 - line 50; claim 9	1-3,5,7, 9,10, 13-15,18
A	GB 1 243 604 A (JEFFERSON CHEMICAL CO., INC.) 25 August 1971 (1971-08-25) page 4, line 101 - line 126; claim 1; table 2	1-4,8-12

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

4 August 2000

Date of mailing of the international search report

14/08/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Angiolini, D

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/09968

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9841554 A	24-09-1998	AU 6558198 A	12-10-1998
		CN 1250454 T	12-04-2000
		EP 0971966 A	19-01-2000
		NO 994496 A	16-09-1999
		PL 335694 A	08-05-2000
US 4507413 A	26-03-1985	DE 3231062 A	23-02-1984
		AT 16505 T	15-11-1985
		CA 1241485 A	30-08-1988
		DE 3361230 D	19-12-1985
		EP 0104377 A	04-04-1984
		ES 525058 D	16-08-1984
		ES 8407082 A	16-11-1984
		HU 35705 A,B	29-07-1985
		JP 1702324 C	14-10-1992
		JP 3070752 B	08-11-1991
GB 1243604 A	25-08-1971	JP 59056461 A	31-03-1984
		DE 2002585 A	27-08-1970
		JP 48032427 B	05-10-1973